

Brand Name	KF 90 NS		اسم المنتج
Product	Assembling Cigarette Adhesive	مادة لاصقة لتجميع الفلتر مع السجائر	المنتج
Lab. Code	ADH – 1 – 4 – 2		كود معلمي

Applications	White emulsion adhesive ready for use. It exhibits a fast setting time, good film flexibility and excellent mechanical stability and dries to a clear film. Recommended for the cigarette manufacturing companies as an assembling adhesive. Especially developed for use on high speed assembling machines (such as Protos 90 S) for highly perforated paper. Packing Rate: 9000 – 1000 cig./minute Productivity: 150.000 – 160.000 cig./kg		مستحلب أبيض جاهز للاستعمال له خصائص لاصقة تظهر سريعاً، يجف إلى طبقة شفافة ومرنه يتميز بثبات ميكانيكي عالي. صمم خصيصاً لشركات تصنيع السجائر. وهي مادة متخصصة للاستعمال على الماكينات السريعة (مثل Protos 90 S) لتجميع الفلتر مع السجارة. سرعة التعبئة: 9000 – 10000 سجارة/دقيقة الانتاجية: 150000 – 160000 سجارة/كيلو		الاستخدامات
	Base	Plasticized synthetic resin dispersion	راتينجات صناعية ملدنة	الأساس	
Properties	Color	White viscous liquid emulsion	مستحلب سائل لزج أبيض	اللون	
	Safety	Food grade - Neither flammable nor toxic – Solvent free.	للإستخدامات الغذائية - غير قابل للاشتعال أو سام - لا يحتوي على مواد طيارة .	الأمان	
Technical Info.	Before drying of the film		قبل جفاف الطبقة اللصق		معلومات فنية
	Solid Content	55 ± 2%	المادة		
	Viscosity	3600 ± 500 cps at 25°C	اللزوجة		
	pH	5 – 6	الرقم		
	Setting time	Fast Drying	زمن	سريع الجفاف	
	After drying of the film		بعد جفاف الطبقة اللصق		
	Appearance	Transparent	المظهر	شفاف	
Elasticity	Elastic	الليونة	مرن		
Shelf life & Storage	Valid for one year from production date if stored in its original tightly closed container in a dry place away from direct sunlight and excessive heat.		صالح لمدة عام من تاريخ الإنتاج المدون، شرط سلامة العبوة، وحفظها بعيداً عن حرارة وأشعة الشمس المباشرة بمكان جيد التهوية.		الصلاحية والتخزين
Packing	25 kg to 125 kg		من 25 الي 125 كجم		التعبئة

Disclaimer: The information & data contained herein are given in good faith but without warranty. We recommend that before using our products, the customer should make his/her own tests to determine the suitability of the products for his/her own purpose under his/her operating conditions. As the circumstances under which our products are stored, handled and used are beyond our control, we cannot assume any responsibility for their use by the customers.