

A-PNT-303 Technical Datasheet

ALKYGLOSS 303

Gloss Enamel Undercoat

DESCRIPTION:

Alkygloss 303 is an alkyd based paint. It is suitable for interior and exterior surfaces as an intermediate coat over anticorrosion primed metal, sealed wood and primed concrete prior to top coating. It exhibits excellent covering capacity, hiding power and adhesion.

PHYSICAL DATA:

Binder : Modified alkyd resin

Pigments : Titanium dioxide and/or colour pigments and functional extenders

Appearance : Gloss

Colour : White and colours

Number of components : One

Specific gravity : Approx. 1.26 Solids by volume : Approx. 50%

Drying times at 30°C : Dust dry : approx. 5 hours

Hard dry : approx. 12 hours Next coat : approx. 24 hours

Flash point : 39 °C

APPLICATION DATA:

Application method : Air spray, brush & roller

Type of thinner : Mineral Spirit

Percentage of thinner : Air spray : 10% max. by volume

Brush and Roller: 5% max. by volume

Dry film thickness per coat : 30 microns

Theo. Coverage at 35 microns DFT : 5.75- 8.5m2/liter or 4-6m2/kg

SHELF LIFE AND STORAGE

12 months from production date if stored in its original tightly closed container in a dry place away from direct sunlight and excessive heat.

Disclaimer: The information & data contained herein are given in good faith but without warranty. We recommend that before using our products, the customer should make his/her own tests to determine the suitability of the products for his/her own purpose under his/her operating conditions. As the circumstances under which our products are stored, handled and used are beyond our control, we cannot assume any responsibility for their use by the customers.

