

A-PNT-505

ALKYMATT 505

Matt Enamel Paint

Technical Datasheet

DESCRIPTION :

Alkymatt 505 is a high quality enamel paint providing a complete flat finish suitable for interior and exterior cement and plastered surfaces. It is also suitable for metal and wood pretreated with an appropriate primer and undercoat. Controlled thixotropic nature of binder facilitates ease of application, freedom from sagging, flow and leveling of film. This product also gives a tough, durable, non yellowing, washable and burnish resistant film.

PHYSICAL DATA:

Binder Pigments Appearance Colours No. of Components Specific gravity Solids by volume Drying times at 30°C		Modified Alkyd Resin Titanium dioxide and/or colour pigments and functional extenders Matt White and Colors One Approx. 1.56 Approx. 52% Touch Dry : 1 hour Hard Dry : 12 hours Recoat : 24 hours
Flash Point	:	39°C
APPLICATION DATA:		
Application method Airless Spray Data Type of Thinner Percentage of Thinner	:	Brush - Roller - Airless Spray – Air Spray Nozzle 0.013", Pressure 150kg/cm ² Mineral Spirit Airless Spray : 3% Max. by volume Air Spray : 10% Max. by volume Brush and Roller : 5 % Max. by volume
Dry Film Thickness per Coat Theo. Coverage at 30 Microns DFT		30 Microns 9.25 – 12.5 m²/liter or 6-8 m²/kg

REMARKS:

- Priming Coats:
 - For steel surfaces: Alkyprime 2001 (Metal Red Oxide Primer)
 - For cement and plastered surfaces: Sealerprime (Latex Sealer Primer)
- Alkymatt 505 can be used as an undercoat when 50 % diluted

SHELF LIFE AND STORAGE

12 months from production date if stored in its original tightly closed container in a dry place away from direct sunlight and excessive heat.

Disclaimer: The information & data contained herein are given in good faith but without warranty. We recommend that before using our products, the customer should make his/her own tests to determine the suitability of the products for his/her own purpose under his/her operating conditions. As the circumstances under which our products are stored, handled and used are beyond our control, we cannot assume any responsibility for their use by the customers.

شركة سياج للكيماويات

الإدارة: ٢١٨ شـارع بور سعيد – الوايلي – القاهرة – جمع. تليفون: ٢٢٥٨٢٦٦٦ - ٢٤٨٢٨٦٦ (٢٠٠) + – فاكس: ٢٢٨٢٦٢٦ (٢٠٢)+ محمول: ١٤ / ٢٨٢٦٦٢ ٥٠٠ (٢٠٠) + – محمول مبيعات ٢٢٧٨٧٨٢٦٢٢(٢٠٢)+ بريد إلكتروني: info@siagchemicals.com – انترنت: www.siagchemicals.com



 Chemicals Company

 871 Port Said Street- El Wally - Cairo – EGYPT

 Tei: +(202) 24828620- 24828656- 24858350 -Fax: +(202) 26833364

 Co.Mobile: +(202) 010 5386813/14- Sales Mobile: +(202) 012 26878526

 E-mail: info@siagchemicals.com